

RINKO & ASSOCIATES, LLC

Materials Chemistry

May 16, 2011

Fellert North America
3411 Brinkerhoff Road
Kansas City, KS 66115

Attn: Sandy Andrew

Ref: Lab File # RA-0414-1A-C-11

1. SAMPLE(S):

Three(3) 7"x 12 ½" x 7/8" sections of Ultra Finish Fellert White 02/01/11 applied on fiberglass board

2. ANALYSIS PERFORMED:

Test for Resistance to Growth of Mold on the Surface of Interior Coatings in an Environmental Chamber – **ASTM D3273**


Test Method for Evaluating Degree of Surface Disfigurement of Paint Films by Microbial (Fungal or Algal) Growth or Soil and Dirt Accumulation – **ASTM D3274**

3. RESULTS:

ASTM D3273/ ASTM D3274

Panel #	Exposure Time			
	1 week	2 weeks	3 weeks	4 weeks
A.	10*	10	10	10
B.	10	10	10	10
C.	10	10	10	10

* Numbers are given as a Disfigurement Rating, where 10 = no growth of Fungus or Algae present.



Robert A. Haffner,
Chief Analytical Chemist/Engineer