

# RINKO & ASSOCIATES, LLC

Materials Chemistry

July 28, 2011

Fellert North America  
3411 Brinkerhoff Road  
Kansas City, KS 66115

Attn: Sandy Andrew

Ref: Lab File # RA-0711-1A-11B

## 1. SAMPLE(S):

One (1) section of Troweled Finish Fellert White 06/06/11

## 2. ANALYSIS PERFORMED:

Sample : Troweled Finish Fellert White 06/06/11

### ASTM E761-92

### ASTM E605-93

Compressive Strength (psi)


Density (lbs/ft<sup>2</sup>)

1. 143  
2. 140  
3. 142

1.84  
1.84  
1.84

**Average      142**

**1.84**



Robert A. Haffner,  
Chief Analytical Chemist/Engineer